

TITLE Formulations of patches Project No.             
Book No. 24

143

From Page No. With Nefegiline free base

with and without 1,2 Propanediol

(#1)

1430 / <sup>26.0</sup> 35 + 1.2 PD / 15 Sel

without 1.2 PD

	solids	liq	1/3 liq
GMS 1430 (41% sol)	85.0	207.3	69.1
1.2 PD	<del>26.0</del> 0.0	0.0	0.0
Sel free base	<del>11.3</del> 15.0	15.0	5.0
Et OH	30.0 <sub>lv</sub>	30.0 <sub>lv</sub>	10.0 <sub>lv</sub>

(#2)

1430 / 35 1.2 PD / 15 Sel

with 1.2 PD

	solids	liq	1/3 liq
GMS 1430 (41%)	50.0	121.95	40.7
1.2 PD	35.0	35.0	11.7
Sel (free base)	15.0	15.0	5.0
Et OH	20.0	20.0	7.0

1.2 PD  
Et OH

To Page No.           

Witnessed & Understood by me,

Date

Invented by

Date

Recorded by

*[Signature]*

Project No. \_\_\_\_\_

Book No. 24

TITLE

Formulation (cont)

TITLE

Pec

From Page No. \_\_\_\_\_

From Page No. \_\_\_\_\_

#3

1753 / ~~20~~ 1.2 PD / 15 Sel

without 1.2 PD

	solids	liqu.	1/3 liqu.
Gelva 1753 (28.3%)	85.0	303.6	101.2
1.2 PD	0.0	0.0	0.0
Sol (free base)	15.0	15.0	5.0
Et OH	30.0 <sub>lv</sub>	30.0 <sub>lv</sub>	10.0 <sub>lv</sub>

Sol was mixed with EtOH and added to 1753 while mixing.

#4

1753 / 35 1.2 PD / 15 Sel

	solids	liqu.	1/3 liqu.
Gelva 1753 / 35 1.2 PD / 15 Sel			
Gelva 1753	50.0	176.75 <sub>lv</sub>	58.94 <sub>lv</sub>
1.2 PD	35.0	35.0	11.7
Sol (free base)	15.0	15.0	5.0
Et OH	20.0	20.0	7.0

EtOH was added to 1753

Sol was mixed with 1.2 PD and added to 1753 while mixing

To Page No. \_\_\_\_\_

Witnessed &amp; Understood by me,

Date

Invented by

Date

Recorded by

Witnessed &amp; Understood by

Liz Coops